The School District of Palm Beach County Project Name SDPBC Project No.

SECTION 04 05 13 MASONRY MORTAR AND GROUT

PART 1 GENERAL

- 1.1 SECTION INCLUDES
 - A. Mortar for Masonry
 - B. Grout for Unit Masonry
- 1.2 REFERENCES
 - A. ACI 530/ASCE 5/TMS 402 Building Code Requirements for Masonry Structures
 - B. ACI 530.1/ASCE 6/TMS 602 Specifications for Masonry Structures
 - C. ASTM C91/C91M Standard Specification for Masonry Cement
 - D. ASTM C94/C94M- Standard Specification for Ready-Mixed Concrete
 - E. ASTM C144 Standard Specification for Aggregate for Masonry Mortar
 - F. ASTM C150/C150M Standard Specification for Portland Cement
 - G. ASTM C207 Standard Specification for Hydrated Lime for Masonry Purposes
 - H. ASTM C270 Standard Specification for Mortar for Unit Masonry
 - I. ASTM C404 Standard Specification for Aggregates for Masonry Grout
 - J. ASTM C476 Standard Specification for Grout for Masonry
 - K. ASTM C595/C595M Standard Specification for Blended Hydraulic Cement
 - L. ASTM C780 Standard Test Method for Preconstruction and Construction Evaluation of Mortars for Plain and Reinforced Unit Masonry
 - M. ASTM C1019 Standard Test Method of Sampling and Testing Grout
 - N. FBC Florida Building Code

1.3 SUBMITTALS

- A. Submit mix design for mortar indicating whether to use the proportion or the property specification of ASTM C270.
- B. Submit mix design for grout indication conformance of grout to requirements of ASTM C476.
- C. Submit test reports indicating conformance of mortar materials to property specifications of ASTM C270.
- D. Submit test reports of pre-construction tests of mortar for consistency, mortar aggregate ratio, water content, air content, compressive strength, and splitting tensile strength in conformance with ASTM C780.
- E. Submit test reports of grout tests in conformance to ASTM C1019.
- F. Submit manufacturer's certificate for products indicating conformance with specified requirements.
- G. Submit two samples representative of mortar color.
- 1.4 DELIVERY, STORAGE, AND HANDLING
 - A. Deliver and store packaged materials in original unopened containers and store in dry weather-tight enclosures.
 - B. Stockpile and handle aggregates to prevent segregation and contamination.
 - C. Maintain sand for volume proportioning of mortar and grout in a damp loose condition.
- 1.5 ENVIRONMENTAL REQUIREMENTS
 - A. Follow requirements of ACI530.1/ASCE6/TMS 602 for cold and hot weather construction.

PART 2 PRODUCTS

- 2.1 MORTAR MATERIALS
 - A. Cementitious Materials:
 - 1. Masonry Cement: ASTM C91/C91M, Type M or S, gray color
 - 2. Portland Cement: ASTM C150/C150M, Type I, gray color

The School District of Palm Beach County Project Name SDPBC Project No.

- 3. Hydrated Lime: ASTM C207, Type S
- B. Sand: ASTM C144
- C. Water: Provide water suitable for drinking, clean, and free of harmful amounts of acid, alkalies, salts, or organic materials.
- D. Admixtures:
 - 1. When required use only non-chloride based accelerators as approved by specifier.
 - 2. Do not add antifreeze substances to the mortar.
- E. Pigments: When required used mineral oxide pigments not to exceed 5% of the weight of masonry cement or 10% of the weight of Portland Cement in the mortar.

2.2 GROUT MATERIALS

- A. Portland Cement: ASTM C150/C150M, Type I
- B. Hydrated Lime: ASTM C207, Type S
- C. Aggregates: ASTM C404
- D. Water: Provide water suitable for drinking, clean, and free of harmful amounts of acid, alkalis, salts, or organic materials.

2.3 MORTAR MIXES

A. Mortar: Provide ASTM C270, type 'M' or type 'S' in conformance with proportion specifications.

2.4 GROUT MIXES

A. Grout: ASTM C476, coarse grout meeting proportion requirements

2.5 MORTAR MIXING

- A. Measure sand by volume or equivalent weight; do not measure by shovel.
- B. In clean mortar mixer, mix ingredients for 3 to 5 minutes with maximum amount of water to produce proper workability.
- C. Re-temper mortar as needed within 2½-hours after initial mixing.
- D. Discard unused mortar 2½-hours after initial mixing.

2.6 GROUT MIXING

- A. Control batching procedure to ensure proper volume proportions of grout materials and achieve grout slump between 8" and 11".
- B. Mix grout in accordance with ASTM C94.
- C. Measure grout materials mixed at job site by volume and mix all ingredients in mechanical mixer for minimum of five minutes.

2.7 MIX TESTS

- A. Testing of Mortar: In accordance with ASTM C270
- B. Testing of Grout: In accordance with ASTM C1019

PART 3 EXECUTION

3.1 INSTALLATION

A. Install mortar and grout in accordance with ACI 530.1/ASCE 6/TMS 602.

3.2 FIELD QUALITY CONTROL

- A. Architect, Owner, or Building Department may request field inspections per Section 01 40 00 1.7 Quality Control.
- B. Test Mortar in accordance with ASTM C780 for consistency, mortar aggregate ratio, water content, air content, compressive strength, and splitting tensile strength.
- C. Test Grout in accordance with ASTM C1019

END OF SECTION